



**ATLAS
TAPES**

ADHESIVE TAPE

Double Sided PP Tape

TECHNICAL DATA SHEET

FILM PROPERTIES

Type of Film

Biaxially Oriented Polypropylene

Film Thickness (μm)

28 ± 2

TM 5006 (Afera)

Tensile Strength MD

100 ± 20 (N/25mm)

TM 5004 by Afera

Elongation at Break

170 ± 40 (%)

TM 5004 by Afera

Liner

Two-sided Siliconized Paper

ATHENS
68 Varis Avenue
16673 Voula, Greece
Tel.: +30 210 8995388

ATALANTI
3rd km Skala Atalanti Road
35200 Atalanti, Greece
Tel.: +30 22330 23725

www.atlas-tapes.gr
info@atlas-tapes.gr

ALL ABOUT TAPES



ADHESIVE PROPERTIES

Type of Adhesive

Hot Melt (Solvent-free)

Peel Adhesion on Stainless Steel

17 ± 4 (N/25mm)

TM 5001 by Afera

Adhesive Color White Transparent

The recommended storage conditions for this product are around 21 °C and 50% relative humidity. Prior to use, carefully check that the contact surfaces are totally dry and clean from oil, grease and dust. The data stated above cannot be considered as binding by contract or by specifications. They correspond to the average values obtained from the tests carried out according to Atlas Tapes norms, in conformity with AFERA norms. Tests are carried out on samples taken from our standard production. These data may vary without any notice – the updated typical value sheets can be forwarded at any time. Since many different factors may influence the product's performance, we recommend testing the product by any application. We remain at your disposal for any further information or recommendations.

Effective: September 2016