


ATHENS 68 Varis Avenue 16673 Voula, Greece Tel.: +30 210 8995388 ATALANTI 3rd km Skala Atalanti Road 35200 Atalanti, Greece Tel.: +30 22330 23725 www.atlas-tapes.gr info@atlas-tapes.gr

ALL ABOUT TAPES

MASKING TAPE SOLVENT MSK 9310 LS

TECHNICAL DATA SHEET



DESCRIPTION:

High-grade automotive masking tape recommended for demanding automotive repair workshops and high degree oven use. Saturated semi crepe paper masking tape coated with specially developed cross-linked solvent based natural rubber adhesive. Guaranteed for one hour, 80°C oven use, also for 100°C 20 minutes. Also suitable for all general masking applications.

APPLICATIONS:

- Guaranteed spray painting automotive oven use in 80°C for 60 minutes.
- · General masking
- · Domestic DIY and industrial general painting
- Holding
- Sealing
- Fixing
- Light duty packaging

PROPERTIES:

- 80° oven use for 60 minutes
- Suitable for both metallic and plastic automotive surfaces
- · Absolute residue free removal
- · Various surface options to cover special requirements
- Excellent tape to tape adhesion
- Solvent and thinner resistant
- High initial tack
- Easy tear
- · Excellent conformability
- Suitable for water and solvent based paints
- Easy curving
- · Easy application on uneven surfaces



NOMINAL VALUES:

Backing

Impregnated Crepe Paper

Adhesive

Solvent-based, Natural Rubber

Tensile Strength MD

90 ± 20 (N/25mm)

TM 5004 by Afera

Elongation at Break MD

9 ± 2 (%)

TM 5004 by Afera

Adhesion to Steel

5 ± I (N/25mm)

TM 5001 by Afera

Rolling Ball Task

Under 2 (cm)

PSTC-6 (PSTC)

Paper thickness

 100 ± 15 (mic)

Total thickness

105 ± 20 (mic)

Application Range

80°C for 60 minutes

Paper Colors White ☐ Sharp Yellow Brown 84

Adhesive Color Transparent